

TECHNICAL DATA SHEET
TERMARUST SERIES TR2100 HRCSA PRIMER TOPCOAT

Technical Data	
Chemistry	High Ratio Co-Polymerized Calcium Sulfonate HRCSA: Contains a minimum of 9.5% active sulfonate, it must maintain a 9-11 to 1 ± 2% ratio Total Base Number to Active Sulfonate. ex. total base number of 85 to 104 to 9.5% Active Sulfonate. ex.as determined by Titration Testing (See Termarust technical dept. for protocols)
System Solvent	Termarust® Thinner TRT01
Color	All colors available on request
Gloss at 60°	15-25° ASTM D523
Mix Ratio	N/A
Viscosity	7000-15000 CPS ASTM D2196 RVT #6 AT 10 RPM
Solids by Weight	72.0% to 79% (depending on color) ASTM D2369
Solids by Volume	61.0% to 68.0% (depending on color) ASTM D2697
Specific Gravity	1.050 – 1.190 (depending on color)
Volatile Organic Compounds (VOC)	240-342 grams per litre (depending on color) 2.00 – 3.42 lbs per gal (depending on color)
Sag Resistance	24 minimum
Dry Film Thickness (DFT)	250 - 300 microns - 10 - 12 mils DFT recoat (on prepared steel) 125-175 microns - 5 - 7 mils DFT overcoat (on existing coatings)
Spread Rate	26.2 sq. m. per litre @ 25 microns DFT 1018 sq. ft. per gal @ 1 mil DFT
Dry Time	12 to 24 hours depending on film thickness and ambient temperature <i>Note: Does not get brittle like conventional paints</i>
Working pot life	N/A
Chemical Resistance	No Hydrocarbon immersion
Thinning	Brush/Roller: Up to 10% with TRT 01 Conventional Spray: 10% with TRT01 Airless Spray: No thinning required
Clean up	Use Termarust Thinner TRT01
Test: 96 HOUR LC50 TROUT	41007 ppm (does not adversely affect marine life)
Weight per gallon	1.056 to 1.193 kg/litre 8.80 to 9.95 pds/US Gal.
Elongation	700%
Shelf life	12 months minimum in original unopened container when stored in a protected area where the temperature is between 5°C and 30°C (41°F - 86°F). <i>Note: After 12 months verify the coating to see if a skin has formed. If a skin is present remove skin and mix the material.</i>

Product Description

Termarust® TR2100 HRCSA High Ratio Co-Polymerized Calcium Sulfonate Primer/Topcoat is a pigmented type of co-polymerized synthetic resin with a unique patented crystalline modification that cures by air oxidation. High Ratio Co-Polymerized Calcium Sulfonate HRCSA coatings are formed by reacting a specific acid, using a proprietary process and a base made of a specific synthetic (grown artificially as opposed to natural crystalline) base material with polymers, to form an active chemistry for the control of corrosion, crevice corrosion and pack rust. This system is ideal for use over minimally prepared surfaces, and is especially suited for coating of flexible structures. High Ratio Co-Polymerized Calcium Sulfonate coatings, designed and engineered exclusively for encapsulation (overcoat) of existing aged leaded paints, vinyl, coal tar epoxy, polyurethanes, epoxy mastics, organic or inorganic zinc, galvanizing, metallizing, acrylics, COR-TEN steel and tightly adhered contaminant free rust, or re-coating of new or prepared structural steel. Ideal for use with high pressure water cleaning, ex. 5000-7000 PSI at 5-6 gallons per minute (preferably hot water).

Uses

Termarust® TR2100 HRCSA High Ratio Co-Polymerized Calcium Sulfonate Primer/Topcoat allows tremendous flexibility in surface profile and preparation. It is ideal for the reclamation and long term protection of bridges, steel structures, highway overpasses, utility towers, cable suspension systems, pipelines, storage tanks and industrial infrastructure.

HRCSA coatings are distributed by Vector Corrosion Technologies on behalf of Termarust Technologies

Termarust manufactures the only HRCSA coatings with a 24 year field history of solving structure critical corrosion on structural steel.

Performance Data	
Cyclic Corrosion	24 hr Freeze-Thaw 360 hr cycle FHWA 2009 (ASTM D5894) @ 4-6 mils DFT, 19 cycles 6840 hours
Salt Spray Resistance	(ASTM B117): @ 4 mils DFT 4000 - 5000 hours with < 2mm creep at the scribe (ASTM D1654) @ 10 mils DFT 8000-10000 hours
QUV Weatherometer	(ASTM 653) @ 4 mils DFT 4000 - 5000 hours. Passes with no peeling, flaking or corrosion
C151B Xenon Arc	@ 4 mils DFT. Passes with no peeling, flaking, or corrosion
K.T.A. Tator Enviro-Test	ASTM Standard Practice draft #1 Date 04-10-92: @ 10 mils DFT SP6-Steel 4445 hours; @ 10 mils DFT Aged Alkyd 1200 hours; @ 5 mils DFT SP6 - Steel 2248 hours; @ 5 mils DFT Aged Alkyd 1520 hours. <i>*All films are pigmented; data may vary depending on formula.</i>

Advantages

Termarust® TR2100 HRCSA High Ratio Co-Polymerized Calcium Sulfonate Primer/Topcoat enhances the following characteristics:

- Advanced technology
- Applicator friendly
- High performance
- Surface tolerant
- Single component
- Non hazardous
- Single coat
- Low VOC
- No hazardous waste stream
- Non-conductive tested to 100 KVA
- Superior Anti-Corrosive Protection
- Field proven performance over 24 years

Termarust® TR2100 HRCSA High Ratio Co-Polymerized Calcium Sulfonate Primer/Topcoat outperforms zinc/epoxy/urethane systems.

Surface Preparation

All grease, oil, grime, and other contaminants must be removed from the surface using commercial detergent or other suitable cleaning method (SSPC-SP1). Hand tool cleaning (SSPC-SP2), power tool cleaning (SSPC-SP3), or high pressure water cleaning (SSPC-WJ4), is sufficient preparation to produce excellent results, SSPC-SP6 or SSPC-WJ3 (L to M) is recommended for immersion service. The prepared surface must be analyzed for Chloride, Nitrate and Sulfate content (Termarust has test kits available). Upper limit Chloride NVC3 3 ug/cm², Sulfate NVS10 10ug/cm², Nitrate NVN10 10ug/cm²

Application

The Termarust® TR2100 HRCSA Primer/Topcoat should not be applied at temperatures below 2°C or 35.6°F. No Coatings should be applied unless the steel surface temperature is 3°C or 5°F above the dew point. Temperature must be maintained during curing. To apply the coating the relative humidity should be no greater than 99% and the steel should be free of surface moisture.

Note: As a touch-up procedure Termarust TR2100 HRCSA Primer/ Topcoat may be applied below freezing (-18°C or 0°F). This is not recommended unless steps are taken to control ice crystals on the steel before application, ex. spot heating. Cold temperatures will slow the coating's cure.

Application Equipment

Airless 15 to 26 tip, Conventional Spray, HVLP, LVLP, Brush, Roller, or Paint Mitt.

Safety Precautions and Regulatory Data

Treat as flammable liquid - Flashpoint 42°C (108°F). Keep away from heat, open flame and sparks. Avoid contact with skin and eyes. Avoid prolonged breathing of vapor. Read label instructions carefully and refer to Material Safety Data Sheet supplied. This product is for industrial use only and is not intended for use in or around a household or dwelling.

Note: all films pigmented, data is formulation dependent.

Canada
Winnipeg, MB
Phone: (204) 489-9611
info@vector-corrosion.com

United States
Lexington, KY
Phone: (813) 830-7566
info@vector-corrosion.com

Europe
Cradley Heath, UK
Phone: (44) 1384 671 400
infoEU@vector-corrosion.com

Middle East
Dubai, UAE
Phone: +971 50 659 7322
infoME@vector-corrosion.com

HRCSA coatings are distributed by Vector Corrosion Technologies on behalf of Termarust Technologies

Termarust manufactures the only HRCSA coatings with a 24 year field history of solving structure critical corrosion on structural steel.

