

Post-Tech[®] PTI Impregnation System

Corrosion Protection System for Grouted/Bonded Post-Tension Tendons

DESCRIPTION

The repair and protection of grouted/bonded post-tension tendons can present unique challenges when a corrosion risk is present due to the presence of voids and defective or contaminated grout. The Post-Tech PTI system has been specifically engineered to mitigate or avert corrosion in bonded post-tension tendons by taking advantage of the naturally occurring interstitial spaces in stranded high strength steel tendons. The Post-Tech PTI corrosion protection material is applied under pressure and travels along the length of the strand while also penetrating into the grout surrounding the wires.

The foundation of the Post-Tech PTI system is a formulated low viscosity dual action hydrocarbon silicon polymer resin. The anti-corrosion Post-Tech PTI impregnation material has a greater affinity to steel surfaces than water and thus displaces moisture from the steel surface to form a protective barrier on any exposed steel surfaces. Further, the impregnation material permeates between the wires of the strand to impregnate the grout surrounding each strand to provide an additional barrier to moisture and oxygen.

The Post-Tech PTI impregnation process can be completed from the end anchorage or from intermediate locations along the length of the tendon. Experience has shown the Post-Tech PTI material can flow through the interstitial spaces at least 250 ft (75m) along the length of a tendon from a single entry point.



Post-Tech PTI impregnation material mitigates corrosion on post-tension strands (right)



Salt spray testing on steel plate with Post-Tech PTI treated section (right)

APPLICATIONS

- Protecting high strength steel strands in bonded posttensioned bridges and other post-tensioned concrete structures
- Grouted stay cables
- Suspension and hangar cables
- Prestressed concrete
 structures

FEATURES AND BENEFITS

- Low viscosity travels under pressure in interstitial spaces along the length of the tendon
- Film forming provides a protective barrier to exposed steel surfaces
- Moisture protection penetrates into grout creating a zone of impregnation around the steel



Impregnation from end of exposed tendon



Impregnation from midpoint location



1/2



Post-Tech[®] PTI Impregnation System

Corrosion Protection System for Grouted/Bonded Post-Tension Tendons

Physical Properties	
Colour	Creamy Amber
Density	7.68 lbs/gal (920 g/L)
Flash Point	144 °F (62 °C)
рН	9 - 10



Post-Tech PTI impregnation occuring through the end cap of a post-tension tendon



Opening in post-tension tendon verifying presence of Post-Tech PTI material around the strands

Vector Corrosion Technologies Ltd. 474B Dovercourt Drive Winnipeg, MB R3Y 1G4 Phone: (204) 489-9611 Fax: (204) 489-6033

info@vector-corrosion.com www.vector-corrosion.com



External tendons being impregnated with Post-Tech PTI material

ABOUT VECTOR

Vector Corrosion Technologies takes pride in offering technically advanced, cost effective corrosion protection solutions to extend the service life and improve the durability of concrete and masonry structures around the world. Vector has earned numerous project awards and patents for product innovation and is committed to a safe, healthy and sustainable environment. For additional information or technical support, please contact any Vector office or our extensive network of international distributors.

Vector Corrosion Technologies, Inc. 8413 Laurel Fair Circle, Suite 200A Tampa, FL 33610

Phone: (813) 830-7566 Fax: (813) 830-7565

info@vector-corrosion.com www.vector-corrosion.com

Vector Corrosion Technologies Limited 27A Upper High Street Cradley Heath, UK B64 5HX Phone: (44) 1384 671 400

infoEU@vector-corrosion.com www.vector-corrosion.eu

Galvashield, Vector and the Vector logo are registered trademarks. Patents: US 9909220, RE40,672 6022469, 6303017, 6193857, and other US and international patents and patents pending. © 2019 Vector Corrosion Technologies. Sept. 25th, 2019



2/2