



Galvashield® XP Product Line

Installation Instructions

INSTALLATION INSTRUCTIONS

The Galvashield XP anodes are designed to mitigate corrosion of reinforcing steel in concrete. In concrete restoration, Galvashield XP anodes are used in locations where an interface between the new repair mortar/concrete and the existing chloride contaminated or carbonated concrete creates a high potential for future corrosion (for more information, refer to “Galvashield Theory” and “Corrosion Management Strategies”). Galvashield XP anodes are simply tied to the existing reinforcing steel along this interface or around the perimeter of the repair area.

For maximum performance, the anodes should be installed as close as practical to the edge of the repair area (within 6 in. or 150mm) while still providing sufficient clearance for the anode to be completely surrounded by the repair mix. Anode spacing shall be as specified by the designer however anode spacing should not exceed 30 inches (750mm) on center. Structures containing heavy reinforcement or exposure to a particularly corrosive environment require reduced spacing (See data sheet for spacing guidelines). For additional information, refer to the Galvashield XP Product Line data sheet or contact Vector Corrosion Technologies.

INSTALLATION PROCEDURE

1. As in standard patch repairs, all old/ loose concrete should be removed from around and behind the steel

reinforcement inside the repair area in accordance with good concrete repair practice. Provide sufficient clearance between the anode and the substrate concrete (minimum of 3/4 in. [19 mm] or 1/4 in. [6 mm] larger than the top size aggregate in the repair material, whichever is greater).

2. The exposed rebar in the repair area shall be thoroughly cleaned to bright metal to facilitate a good electrical connection where anodes will be attached. Prior to installation, electrical continuity of the rebar within the repair area should be confirmed with the use of an appropriate meter.

Note: When checking electrical continuity DC resistance of 1 ohm or a potential difference of 1 mV or less is acceptable. Discontinuities can be corrected by wiring the “unconnected” bar to adjacent bars using standard steel tie wire.

3. Securely fasten anode in place with attached tie wires. If the anode is to be tied onto a single bar, or if less than 1 inch (25 mm) of concrete cover exists, place anode beneath the bar (away from the surface of the concrete). If sufficient cover exists, the anode may be placed at the intersection between two bars and secured to each clean bar. Galvashield XP2 and XP4 anodes with the BarFit™ groove and Galvashield XPT anodes are placed along side the steel.

4. Once installed, electrical continuity between the anode tie wires and the rebar should be confirmed using an

appropriate meter. Maximum DC resistance of 1 ohm or potential difference of 1mV.

5. Repair material must have a resistivity below 50,000 ohm•cm. Products with significant polymer modification and/or silica fume content may not be suitable. Similarly, if bonding agents are used, they should have suitable conductivity. Insulating materials such as epoxy bonding agents should not be used. If high resistance repair materials are to be used, anodes should be installed with Galvashield Embedding Mortar (contact Vector for further details).

Note: If rebar coatings are to be used, care should be taken to ensure the anode and tie wires do not become coated or the connection between the anode tie wires and the rebar is not lost.

6. Complete the repair following normal concrete repair procedures, taking care not to create any voids around the anode. Do not soak the anode units for greater than 20 minutes.

HEALTH AND SAFETY

As with all cement-based materials, contact with moisture can release alkalis which may be harmful to exposed skin. Galvashield anode units and Galvashield Embedding Mortar should be handled with suitable gloves and other personal protective equipment in accordance with standard procedures for handling cementitious materials. Additional safety information is included in the Material Safety Data Sheet.

Vector Corrosion Technologies Ltd.

474B Dovercourt Drive
Winnipeg, MB R3Y 1G4
Phone: (204) 489-9611
Fax: (204) 489-6033

info@vector-corrosion.com
www.vector-corrosion.com

Vector Corrosion Technologies, Inc.

8413 Laurel Fair Circle, Suite 200A
Tampa, FL 33610
Phone: (813) 830-7566
Fax: (813) 830-7565

info@vector-corrosion.com
www.vector-corrosion.com

Vector Corrosion Technologies Limited

27A Upper High Street
Cradley Heath, UK B64 5HX
Phone: (44) 1384 671 400

infoEU@vector-corrosion.com
www.vector-corrosion.eu

